HISAN



HS200 *Chromium Carbide Overlay Wear Plates*

HS200, manufactured using submerged arc welding technology and powder metallurgy cladding technology, a high concentration of chromium carbides is uniformly clad onto a mild steel backing material and evenly distributed throughout the uniform thickness of the overlay layer, achieving exceptional wear resistance while maintaining excellent ductility and enabling forming and welding capabilities.

HS200 performs very well under severe abrasion environments.

- ***Bulk Hardness: HRC 58-65***
- ***Abrasion Test result: ≤ 0.18g(testing under ASTM G65, procedure A)***

TYPICAL PROPERTIES

Element	C	Si	Mn	Cr	Others
Content	3.5-7.5%	0.5-2.5%	0.5-2.5%	30-40%	Bal

SIZE

Standard plate size(mm)	1400*3000	1400*3500	1500*3000	2000*3000	2100*3500	2100*6000	2200*11000
Overlay thickness(mm)	3-80						
Base material thickness(mm)	3-150						
Common thickness Base+Overlay(mm)	3+3 4+4...6+4 6+6 8+6 8+8 10+9 10+10 8+12 12+12... 12+17 10+20 12+30...14+40 16+50 20+80...						

Other sizes and thicknesses available on request.







HISAN (Tianjin) Co., Ltd
+86 22 84776558
hs@hisantech.com
hisantech.com
No.3, Xingang Wuhao Road, Jinnan District, Tianjin, China

FABRICATION

The backing steel plate provides Hisan plates with structural integrity, which makes our overlay plates fabricated without damage to the welding overlay, regardless of the shape and complexity of the structure. Hisan has the capability to manufacture cut to size wear parts, fabrication includes:

Cutting, Punching



Bending



Bolting

Assembling



APPLICATION

The overlay plate is widely used in mining, iron&steel, port, cement, concrete, aggregate, asphalt, coal-fired power, metal recycling, glass production, sugar, dredging, foundry, pulp and paper industries. Different overlay grades are available to suit various working conditions.

HISAN (Tianjin) Co., Ltd
+86 22 84776558
hs@hisantech.com
hisantech.com
No.3, Xingang Wuhao Road, Jinnan District, Tianjin, China